Application No.: 10/564,440

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1.-4. (canceled).

5. (currently amended): The process for producing a catalyst for the production of acetic acid as elaimed in claim 3, the catalyst being a supported catalyst which is used in a process for producing acetic acid by reacting ethylene and oxygen in a gas phase and comprises (a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof and (c) at least one element selected from the group consisting of Sn. Pb. Bi, Sb and Te, the process comprising loading palladium in parts and through at least two steps, which comprises the following first and second steps:

First Step:

a step of loading (a) palladium on a support to obtain a palladium-supported catalyst;

Second Step:

a step of loading (a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof and (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te on the palladium-supported catalyst obtained in the first step to obtain a catalyst for the production of acetic acid.

Application No.: 10/564,440

6. (currently amended): The process for producing a catalyst for the production of acetic acid as elaimed in claim 3, the catalyst being a supported catalyst which is used in a process for producing acetic acid by reacting ethylene and oxygen in a gas phase and comprises
(a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof and (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te, the process comprising loading palladium in parts and through at least two steps, which comprises the following first, second and third steps:

First Step:

a step of loading (a) palladium on a support to obtain a palladium-supported catalyst;

Second Step:

a step of loading (c) at least one element selected from the group consisting of Sn,

Pb, Bi, Sb and Te on the palladium-supported catalyst obtained in the first step to obtain a

palladium-supported catalyst containing an element of the group (c);

Third Step:

a step of loading (a) palladium and (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof on the palladium-supported catalyst containing an element of the group (c) obtained in the second step to obtain a catalyst for the production of acetic acid.

7.-8. (canceled).

Application No.: 10/564,440

9. (currently amended): The process for producing a catalyst for the production of acetic acid as elaimed in claim 7, the catalyst being a supported catalyst which is used in a process for producing acetic acid by reacting ethylene and oxygen in a gas phase and comprises (a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof, (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn, the process comprising loading palladium in parts and through at least two steps, which comprises the following first and second steps:

First Step:

a step of loading (a) palladium and (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te on a support to obtain a palladium-supported catalyst;

Second Step:

a step of loading (a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn on the palladium-supported catalyst containing an element of the group (c) obtained in the first step to obtain a catalyst for the production of acetic acid.

10. (currently amended): The process for producing a catalyst for the production of acetic acid as elaimed in claim 7, the catalyst being a supported catalyst which is used in a process for producing acetic acid by reacting ethylene and oxygen in a gas phase and comprises
(a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids

Application No.: 10/564,440

and salts thereof. (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn, the process comprising loading palladium in parts and through at least two steps, which comprises the following first and second steps:

First Step:

a step of loading (a) palladium and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn on a support to obtain a palladium-supported catalyst;

Second Step:

a step of loading (a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof and (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te on the palladium-supported catalyst containing an element of the group (d) obtained in the first step to obtain a catalyst for the production of acetic acid.

11. (currently amended): The process for producing a catalyst for the production of acetic acid as elaimed in elaim 7, the catalyst being a supported catalyst which is used in a process for producing acetic acid by reacting ethylene and oxygen in a gas phase and comprises

(a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof, (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au

Application No.: 10/564,440

and Zn, the process comprising loading palladium in parts and through at least two steps, which comprises the following first and second steps:

First Step:

a step of loading (a) palladium on a support to obtain a palladium-supported catalyst;

Second Step:

a step of loading (a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof, (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn on the palladium-supported catalyst obtained in the first step to obtain a catalyst for the production of acetic acid.

12. (currently amended): The process for producing a catalyst for the production of acetic acid as elaimed in elaim 7, the catalyst being a supported catalyst which is used in a process for producing acetic acid by reacting ethylene and oxygen in a gas phase and comprises (a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof, (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn, the process comprising loading palladium in parts and through at least two steps, which comprises the following first, second and third steps:

First Step:

Application No.: 10/564,440

a step of loading (a) palladium and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn on a support to obtain a palladium-supported catalyst;

Second Step:

a step of loading (c) at least one element selected from the group consisting of Sn,
Pb, Bi, Sb and Te on the palladium-supported catalyst containing an element of the group (d)
obtained in the first step to obtain a palladium-supported catalyst containing an element of the
group (c) and an element of the group (d);

Third Step:

a step of loading (a) palladium and (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof on the palladium-supported catalyst containing an element of the group (c) and an element of the group (d) obtained in the second step to obtain a catalyst for the production of acetic acid.

13. (currently amended): The process for producing a catalyst for the production of acetic acid as elaimed in elaim 7, the catalyst being a supported catalyst which is used in a process for producing acetic acid by reacting ethylene and oxygen in a gas phase and comprises (a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof, (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn, the process comprising loading palladium in parts and through at least two steps, which comprises the following first, second and third steps:

AMENDMENT UNDER 37 C.F.R. § 1.111 Attorney Docket No.: Q77244
Application No.: 10/564,440

First Step:

a step of loading (a) palladium on a support to obtain a palladium-supported catalyst;

Second Step:

a step of loading (c) at least one element selected from the group consisting of Sn,
Pb, Bi, Sb and Te on the palladium-supported catalyst obtained in the first step to obtain a
palladium-supported catalyst containing an element of the group (c);

Third Step:

a step of loading (a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn on the palladium-supported catalyst containing an element of the group (c) obtained in the second step to obtain a catalyst for the production of acetic acid.

14.-20. (canceled).

21. (currently amended): The process for producing a catalyst for the production of acetic acid as claimed in claim 1, the catalyst being a supported catalyst which is used in a process for producing acetic acid by reacting ethylene and oxygen in a gas phase and comprises

(a) palladium and (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof, the process comprising loading palladium in parts and through at least two steps, including the following first and second steps:

Application No.: 10/564,440

First Step:
a step of loading (a) palladium on a support to obtain a palladium-supported
catalyst;
Second Step:
a step of loading (a) palladium and (b) at least one compound selected from the
group consisting of heteropolyacids and salts thereof on the palladium-supported catalyst
obtained in the first step to obtain a catalyst for the production of acetic acid,

wherein the first step further comprises the following first-1, first-2 and first-3 steps:

First-1 Step:

a step of loading (a) a palladium compound on a support to obtain a palladiumsupported catalyst;

First-2 Step:

a step of dipping the palladium-supported catalyst obtained in the first-1 step in an aqueous alkali solution;

First-3 Step:

a step of reducing the palladium-supported catalyst obtained in the first-2 step to obtain a metal palladium-supported catalyst.

22. (currently amended): The process for producing a catalyst for the production of acetic acid as claimed in claim 3, the catalyst being a supported catalyst which is used in a process for producing acetic acid by reacting ethylene and oxygen in a gas phase and comprises
(a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids

Application No.: 10/564,440

and salts thereof and (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te, the process comprising loading palladium in parts and through at least two steps including the following first and second steps:

First Step:

a step of loading (a) palladium and (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te on a support to obtain a palladium-supported catalyst;

Second Step:

a step of loading (a) palladium and (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof on the palladium-supported catalyst containing an element of the group (c) obtained in the first step to obtain a catalyst for the production of acetic acid,

wherein the first step further comprises the following first-1, first-2 and first-3 steps:

First-1 Step:

a step of loading (a) a palladium compound and (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te on a support to obtain a palladium-supported catalyst;

First-2 Step:

a step of dipping the palladium-supported catalyst containing an element of the group (c) obtained in the first-1 step in an aqueous alkali solution;

First-3 Step:

Application No.: 10/564,440

a step of reducing the palladium-supported catalyst containing an element of the group (c) obtained in the first-2 step to obtain a metal palladium-supported catalyst containing an element of the group (c).

23. (previously presented): The process for producing a catalyst for the production of acetic acid as claimed in claim 10, wherein the first step further comprises the following first-1, first-2 and first-3 steps:

First-1 Step:

a step of loading (a) a palladium compound and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn on a support to obtain a palladium-supported catalyst;

First-2 Step:

a step of dipping the palladium-supported catalyst containing an element of the group (d) obtained in the first-1 step in an aqueous alkali solution;

First-3 Step:

a step of reducing the palladium-supported catalyst containing an element of the group (d) obtained in the first-2 step to obtain a metal palladium-supported catalyst containing an element of the group (d).

24. (currently amended): The process for producing a catalyst for the production of acetic acid as elaimed in claim 7, the catalyst being a supported catalyst which is used in a process for producing acetic acid by reacting ethylene and oxygen in a gas phase and comprises

Application No.: 10/564,440

(a) palladium, (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof, (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn, the process comprising loading palladium in parts and through at least two steps. including the following first and second steps:

First Step:

a step of loading (a) palladium, (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn on a support to obtain a palladium-supported catalyst;

Second Step:

a step of loading (a) palladium and (b) at least one compound selected from the group consisting of heteropolyacids and salts thereof on the palladium-supported catalyst containing an element of the group (c) and an element of the group (d) obtained in the first step to obtain a catalyst for the production of acetic acid.

wherein the first step further comprises the following first-1, first-2 and first-3 steps:

First-1 Step:

a step of loading (a) a palladium compound, (c) at least one element selected from the group consisting of Sn, Pb, Bi, Sb and Te and (d) at least one element selected from the group consisting of Cr, Mn, Fe, Ru, Co, Cu, Au and Zn on a support to obtain a palladium-supported catalyst;

First-2 Step:

Application No.: 10/564,440

a step of dipping the palladium-supported catalyst containing an element of the group (c) and an element of the group (d) obtained in the first-1 step in an aqueous alkali

solution;

First-3 Step:

a step of reducing the palladium-supported catalyst containing an element of the

group (c) and an element of the group (d) obtained in the first-2 step to obtain a metal palladium-

supported catalyst containing an element of the group (c) and an element of the group (d).

25. (currently amended): The process for producing a catalyst for the production of

acetic acid as claimed in claim 5[[1]], wherein (b) the heteropolyacid or a salt thereof is selected

from the following heteropolyacids and salts thereof:

1-12-phosphotungstic acid: H₃[PW₁₂O₄₀]·nH₂O

1-12-silicotungstic acid: H4[SiW12O40]·nH2O

wherein n represents an integer of 0 to 40.

26. (currently amended): A catalyst for the production of acetic acid, which is

obtained by the process for producing a catalyst for the production of acetic acid as set forth in

claim 5[[1]].

(original): A process for producing acetic acid, comprising reacting ethylene and

oxygen in a gas phase in the presence of the catalyst for the production of acetic acid as set forth

in claim 26 obtained by the process for producing a catalyst for the production of acetic acid.

13